



# Determination of the lower critical field $H_{c1}(T)$ in FeSe single crystals by magnetization measurements



Mahmoud Abdel-Hafiez<sup>a,b,\*</sup>, Alexander N. Vasiliev<sup>c,d</sup>, Dmitriy A. Chareev<sup>e</sup>, Victor V. Moshchalkov<sup>f</sup>, Alejandro V. Silhanek<sup>a</sup>

<sup>a</sup> Département de Physique, Université de Liège, B-4000 Sart Tilman, Belgium

<sup>b</sup> Physics department, Faculty of science, Fayoum University, 63514 Fayoum, Egypt

<sup>c</sup> Low Temperature Physics and Superconductivity Department, Physics Faculty, M.V. Lomonosov Moscow State University, 119991 Moscow, Russia

<sup>d</sup> Theoretical Physics and Applied Mathematics Department, Ural Federal University, 620002 Ekaterinburg, Russia

<sup>e</sup> Institute of Experimental Mineralogy, Russian Academy of Sciences, Chernogolovka, Moscow 142432, Russia

<sup>f</sup> INPAC - Institute for Nanoscale Physics and Chemistry, KU Leuven, Celestijnenlaan 200D, B-3001 Leuven, Belgium

## ARTICLE INFO

### Article history:

Received 31 December 2013

Received in revised form 10 April 2014

Accepted 11 April 2014

Available online 21 April 2014

### Keywords:

FeSe superconductor

Single crystal

Magnetic properties

Lower critical field

## ABSTRACT

In a recent work, Abdel-Hafiez et al. [1] we have determined the temperature dependence of the lower critical field  $H_{c1}(T)$  of a FeSe single crystal under static magnetic fields  $H$  parallel to the crystallographic  $c$  axis. The temperature dependence of the first vortex penetration field has been experimentally obtained by two independent methods and the corresponding  $H_{c1}(T)$  was deduced by taking into account demagnetization factors. In general, the first vortex penetration field may not reflect the true  $H_{c1}(T)$  due to the presence of surface barriers. In this work we show that magnetic hysteresis loops are very symmetric close to the critical temperature  $T_c = 9$  K evidencing the absence of surface barriers and thus validating the previously reported determination of  $H_{c1}(T)$  and the main observations that the superconducting energy gap in FeSe is nodeless.

© 2014 Elsevier B.V. All rights reserved.

## 1. Introduction

At low applied magnetic fields  $H$ , a bulk type-II superconductor can expel the magnetic field from its interior by means of screening supercurrents running typically in a submicron layer of width  $\lambda$  from the sample's borders [2,3]. As  $H$  increases, the kinetic energy of the superelectrons increases until at a certain field  $H_{c1}(T)$  it becomes favorable to allow quantum units of flux to penetrate into the superconductor thus relaxing the magnetic pressure. Eventually, at an even higher field,  $H_{c2}$ , the vortex core of neighboring vortices overlap, and the sample reestablishes the normal metallic behavior. This description of the magnetic response of a superconductor holds within the thermodynamic limit, i.e. large volumes and homogeneous fields, but requires some revision if we include geometrical details of the sample through demagnetization factors and surface boundary effects. Indeed, in case of perfectly flat surface boundaries, it has been shown that the entrance of vortices can be delayed up to the thermodynamic critical field [4]

$H_c = \sqrt{H_{c1}H_{c2}} \ll H_{c1}$  and moreover the ultimate vestige of superconductivity can be found at fields surpassing by almost 70% the upper critical field  $H_{c2}$  [5]. In other words, surface effects can severely modify the overall behavior of the superconducting state.

The determination of  $H_{c1}$  is of primary importance since it allows one to extract the magnetic penetration depth  $\lambda$  fundamental parameter characterizing the superconducting condensate and carrying information about the underlying pairing mechanism. A popular approach to measure  $H_{c1}$  consists of measuring the magnetization  $M$  as a function of  $H$  and then identify the deviation of the linear Meissner response which would correspond to the vortex penetration. This technique implicitly relies on the assumption that no surface barriers are present, thus assuring that  $H_{c1}$  coincides with vortex penetration.

Although  $s^\pm$ -pairing has been suggested for Fe-based superconductors, the pairing mechanism of superconductivity in these materials remains one of the most important open questions [6–10]. In a recent work, Abdel-Hafiez et al. [1] determined  $H_{c1}$  in FeSe single crystal from the onset of either the trapped moment or the nonlinear  $M(H)$  response. This analysis and the main conclusion of that work, i.e. that FeSe has a nodeless superconducting gap, remain partially uncertain unless evidence of absence of surface barrier in this particular crystal is brought up. In this work, it is

\* Corresponding author at: Département de Physique, Université de Liège, B-4000 Sart Tilman, Belgium. Tel.: +32 43663716; fax: +32 43663629.

E-mail addresses: [m.mohamed@ulg.ac.be](mailto:m.mohamed@ulg.ac.be), [mahmoudhafiez@gmail.com](mailto:mahmoudhafiez@gmail.com) (M. Abdel-Hafiez).

precisely this issue that we address and, we demonstrate that the fact that magnetization loops exhibit no asymmetries with respect to  $M = 0$ , strongly suggests that surface barriers are of little relevance showing that first vortex penetration occurs at  $H_{c1}$  [11].

## 2. Experimental


Magnetic susceptibilities were performed on a FeSe single crystal of rectangular shape rectangular with short dimension single crystal, which has lateral dimensions  $a \times b \times c = 1.05 \pm 0.08 \times 1.25 \pm 0.1 \times 0.02 \pm 0.1 \text{ mm}^3$  and a mass of 1.2 mg. The investigated plate-like FeSe crystal grown was grown in an evacuated quartz ampoule using the  $\text{AlCl}_3\text{KCl}$  flux technique with a constant temperature gradient of  $5^\circ\text{C}/\text{cm}$  along the ampoule length temperature of the hot end was kept at  $427^\circ\text{C}$ , temperature of the cold end was about  $380^\circ\text{C}$ . The phase purity of the resulting crystal was checked with X-ray diffraction [12]. Magnetization measurements were performed using a superconducting quantum interference device magnetometer (MPMS-XL5) from Quantum Design.

## 3. Results and discussions


The main panel of Fig. 1 presents the temperature dependence of the isothermal magnetization  $M$  at  $H = 100 \text{ Oe}$  parallel to  $c$ . The zero-field cooled (ZFC) data above the superconducting transition temperature  $T_c$  displays a larger susceptibility and diamagnetic-like temperature dependence of the magnetic susceptibility as that observed in [13], which indicates the itinerant nature of electronic states of Fe at the Fermi energy. The inset shows the temperature dependence of the magnetic susceptibility measured by following ZFC and field-cooled (FC) procedures in an external field of  $1 \text{ Oe}$  applied along  $c$ . The ZFC data show a sharp diamagnetic signal, thus confirming bulk superconductivity in FeSe single crystal. The magnetic susceptibility exhibits a superconducting transition with an onset transition temperature  $T = 9.4 \text{ K}$ .

Fig. 2(a) presents the field dependence of the critical current density  $J_c$  at various temperatures up to  $40 \text{ kOe}$  for  $H$  parallel  $c$  and  $H$  parallel  $ab$  (see the inset of Fig. 2(a)). For  $H$  parallel  $c$ , the magnetic irreversibility presents a second peak at  $T = 2 \text{ K}$ . Whereas no second peak is observed for  $H$  parallel  $ab$ .

From the magnetization hysteresis loops  $M(H)$  as recently reported in [1], we calculate the  $J_c$  of both orientation by using the critical state model with the assumption of field-independent  $J_c$ .



**Fig. 1.** The main panel shows the temperature dependence of the isothermal magnetization  $M$  vs.  $T$  measured with the field parallel to both  $c$  axis of  $1 \text{ kOe}$ . The inset presents the temperature dependence of the magnetic susceptibility after demagnetization correction in an external field of  $1 \text{ Oe}$  applied along  $c$  following ZFC and FC protocols for FeSe single crystals.




**Fig. 2.** (a) The critical current density  $J_c$  at various temperatures up to  $40 \text{ kOe}$  for  $H$  parallel  $c$ . The inset presents the  $J_c$  values for  $H$  parallel  $ab$ . (b) Temperature dependence of the critical current density  $J_c$  values at  $H = 0$  of both orientation for the FeSe single crystal. The line is a guide to the eyes.

$$J_c = \frac{20\Delta M}{a(1 - a/3b)} \quad (1)$$

where  $\Delta M = M_{\text{dn}} - M_{\text{up}}$ ,  $M_{\text{dn}}$  and  $M_{\text{up}}$  are the magnetization measured with decreasing and increasing applied field, respectively,  $a$  (cm) and  $b$  (cm) are sample widths ( $a < b$ ). The unit of  $\Delta M$  is in electromagnetic unit per cubic centimeter and the calculated  $J_c$  is in Ampere per square centimeter. We obtain  $J_c(2 \text{ K}) \sim 1.34 \times 10^4 \text{ A/cm}^2$  for  $H$  parallel  $c$  and  $J_c(2 \text{ K}) \sim 1.8 \times 10^4 \text{ A/cm}^2$  for  $H$  parallel  $ab$ . These values are lower than those reported in Ba-122, 1111, 11, and the 111 systems [14–17] and higher than those observed in  $\text{K}_{0.64}\text{Fe}_{1.44}\text{Se}_2$  [18]. Fig. 2(b) summarizes the temperature dependence of the  $J_c$  value at  $H = 0$  for both orientation and one can clearly see a strong temperature dependence of  $J_c$  at  $H = 0$ .

One may argue that the nominal  $H_{c1}$  values obtained with our experiment either by the trapped moment  $M_t$  or nonlinear  $M(H)$  response in FeSe studies in [1] may not reflect the true  $H_{c1}$  but the flux entry field because of the Bean–Livingston surface barrier [11]. However, it is clear that the influence of surface barrier is not important in our investigated single crystal since: (i) the magnetic hysteresis loops are very symmetric close to  $T_c$ , see Fig. 3 as well as the lower and upper inset for  $8.5$  and  $9 \text{ K}$ , respectively. (ii) an extremely small and unreasonable  $H_{c1}$  will be obtained when following the scenario of the Bean–Livingston surface barrier:  $H_c = \frac{kH_{c1}}{\ln k}$  assuming  $k \sim 72.3$ . Therefore, if the surface barrier should be taken into account, the true  $H_{c1}$  would be much smaller than the one studied in [1]. (iii) the lower critical field has been obtained on a high quality single crystal. Therefore, due to the latter reasons the Bean–Livingston barrier is not important in our present sample. It is worth mentioning that recently, multiple Andreev reflections spectroscopy [12] and angle-resolved photoemission spectroscopy (ARPES) [19] as well as specific-heat measurements [20] also gave



**Fig. 3.** Magnetic field dependence of magnetization in FeSe single crystal at different temperatures ranging from 6.5, 7, 7.5, to 8.5 K. The lower and upper inset shows the full magnetic hysteresis loops of 8.5 and 9 K, respectively.

results consistent with the good quality of our investigated single crystal.

#### 4. Summary

In conclusion, we have measured the  $M$ – $H$  curve of a high-quality FeSe single crystal close to  $T_c$  and found out that the magnetic hysteresis loops are symmetric. We calculated the critical current density of both orientation and the values are found to be  $J_c$  (2 K)  $\sim 1.34 \times 10^4$  A/cm<sup>2</sup> for  $H$  parallel  $c$  and  $J_c$  (2 K)  $\sim 1.8 \times 10^4$  A/cm<sup>2</sup> for  $H$  parallel  $ab$ .

#### Acknowledgments

This work is supported by the FNRS projects, “crédit de démarrage U.Lg”, the MP1201 COST Action and by the Methusalem Funding of the Flemish Government. The work of A.N.V. and D.A.C. was supported by RFBR Grants 13-02-00174 and 12-02-90405.

#### References

- [1] M. Abdel-Hafiez, J. Ge, A. Vasiliev, D. Chareev, J. Van de Vondel, V.V. Moshchalkov, A.V. Silhanek, *Phys. Rev. B* 88 (2013) 174512.
- [2] M. Tinkham, *Introduction to Superconductivity*, Dover, New York, 1996.
- [3] K. Fossheim, A. Sudbo, *Superconductivity Physics and Applications*, The Norwegian University of Science and Technology Trondheim, Norway, 2004.
- [4] J. Gutierrez, B. Raes, J. Van de Vondel, A.V. Silhanek, R.B.G. Kramer, G.W. Ataklti, V.V. Moshchalkov, *Phys. Rev. B* 88 (2013) 184504.
- [5] R.G. Mints, I.B. Snapiro, *Phys. Rev. B* 47 (1993) 3273.
- [6] I.I. Mazin, *Nature* 464 (2010) 183.
- [7] M. Abdel-Hafiez et al., *Phys. Rev. B* 87 (2013) 180507(R).
- [8] F. Hardy et al., *Phys. Rev. Lett.* 111 (2013) 27002.
- [9] M. Abdel-Hafiez et al., *Phys. Rev. B* 85 (2012) 134533.
- [10] M. Abdel-Hafiez et al., *J. Phys.: Conf. Ser.* 391 (2012) 012120.
- [11] C.P. Bean, J.D. Livingston, *Phys. Rev. Lett.* 12 (1964) 14.
- [12] D. Chareev, E. Osadchii, T. Kuzmichev, J.-Y. Lin, S. Kuzmichev, O. Volkova, A. Vasiliev, *Cryst. Eng. Comm.* 15 (2013) 1989.
- [13] G.E. Grechnev, A.S. Panfilov, V.A. Desnenko, A.V. Fedorchenko, S.L. Gnatchenko, D.A. Chareev, O.S. Volkova, A.N. Vasiliev, *J. Phys.: Condens. Matter* 25 (2013) 046004.
- [14] B. Shen, P. Cheng, Z. Wang, L. Fang, C. Ren, L. Shan, H.-H. Wen, *Phys. Rev. B* 81 (2010) 014503.
- [15] D. Bhoi, P. Mandal, P. Choudhury, S. Dash, A. Banerjee, *Physica C: Supercond.* 471 (2011) 258.
- [16] R.W. Hu, E.S. Bozin, J.B. Warren, C. Petrovic, *Phys. Rev. B* 80 (2009) 214514.
- [17] A.K. Pramanik, L. Harnagea, C. Naeke, A.U.B. Wolter, S. Wurmehl, V. Kataev, B. Büchner, *Phys. Rev. B* 83 (2011) 094502.
- [18] H. Lei, C. Petrovic, *Phys. Rev. B* 83 (2011) 184504.
- [19] J. Maletz, V. B. Zabolotnyy, D. V. Evtushinsky, S. Thirupathaiah, A. U. B. Wolter, L. Harnagea, A. N. Yaresko, A. N. Vasiliev, D. A. Chareev, E. D. L. Rienks, B. Büchner, S. V. Borisenko, (2013), *ArXiv:1307.1280*.
- [20] J.-Y. Lin, Y.S. Hsieh, D.A. Chareev, A.N. Vasiliev, Y. Parsons, H.D. Yang, *Phys. Rev. B* 84 (2011) 220507(R).